

Opustone[®]
STONE | TILE CONCEPTS

RELATIVA

PORCELAIN TILES



*Product Shown Below
Vena Grigio Light 24"x48" Natural*

*Product Shown on Cover
Travertino Neve 24"x48" Natural*

RELATIVA

INSPIRED BY NATURE

Relativa porcelain tiles are a tribute to the enduring beauty and strength of natural stone, reimagined through the lens of contemporary design and technological innovation.



Product Shown
Taj Mahal 48"x48" Satin

More than a simple surface, Relativa
embodies the harmony of contrasts:
strength and grace, heritage and progress.

CALACATTA BORGHINI



AVAILABLE TILES

24" x 48" Satin

48" x 48" Satin

TRAVERTINO NEVE



AVAILABLE TILES

24" x 48" Natural

48" x 48" Natural

Product Shown
Atacama Gris 24"x48" Satin

Offering the resilience needed for
modern environments.

VENA GRIGIO LIGHT



AVAILABLE TILES
24" x 48" Natural

ATACAMA GRIS



AVAILABLE TILES
24" x 48" Satin

Product Shown on Floor
Travertino Neve 48"x48" Natural



With the versatility that allows for
visually seamless applications.

TAJ MAHAL



AVAILABLE TILES
24" x 48" Satin
48" x 48" Satin

BRECCIA IMPERIALE



AVAILABLE TILES
24" x 48" Satin

Embued with organic variations and characteristics of natural stone.



TECHNICAL INFORMATION			
INTERNATIONAL STANDARDS	TEST METHOD	AVAILABLE FINISH	
		9MM NATURAL	9MM SATIN
N/A	Shade Variation	V3	V3
ISO 10545-3	Water Absorption Individual Maximum (in % by mass)	<= 0.1%	<= 0.1%
ASTM C373	Water Absorption Max (in % by mass)	<= 0.5%	<= 0.5%
ISO 10545-4	Breaking Strength	S >= 1500 N	S >= 1000 N
ISO 10545-4	Bending Resistance	R >= 40 N/mm ²	R >= 40 N/mm ²
ISO 10545-5	Impact Resistance, as coefficient of restitution (Declared Value)	>= 0.55	>= 0.55
ISO 10545-6	Resistance to deep abrasion of unglazed tiles (removed volume)	<= 150mm ³	<= 150mm ³
ISO 10545-8	Coefficient of thermal linear expansion (Declared Value)	<= 7MK-1	<= 7MK-1
ISO 10545-9	Thermal Shock Resistance	Resistant	Resistant
ISO 10545-10	Moisture Expansion (in mm/m)	<=0.01% (0.1mm/m)	<=0.01% (0.1mm/m)
ISO 10545-12	Frost Resistance	Resistant	Resistant
EN 12004-2	Bond strength/adhesion for cementitious adhesives (Declared Value)	>=1.0 N/mm ² (Class C2 - EN 12004)	>=1.0 N/mm ² (Class C2 - EN 12004)
N/A	Reaction to Fire	A1 - A1fl	A1 - A1fl
ISO 10545-13	Resistance to household chemicals and swimming pool salts (Minimum Class B)	A	A
ISO 10545-13	Resistance to low concentration of acids and alkalis (Declared Class)	LA	LA
ISO 10545-14	Resistance to staining, for unglazed tiles (Declared Class)	5	>= 3
DIN EN 16165 Annex B (EX DIN 51130)	Shood Ramp Test (Declared Value)	R10	R9
DIN EN 16165 Annex A (EX DIN 51097)	Barefoot Ramp Test (Declared Value)	A+B	N/A
BS EN 16165 Annex C (EX BS 7976)	Pendulum Friction Test (PTV >= 36 classifies the surface as low slip risk)	>= 36 Dry >= 36 Wet	>= 36 Dry <= 24 Wet
B.C.R.A. Rep. CEC/81	Coefficient of Friction - COF (D. M. 236/89 del 14/06/89)	>0.40 Dry <0.40 Wet	>0.40 Dry <0.40 Wet
ANSI A 326,3	Coefficient of Friction - DCOF	Wet DCOF >= 0.50	Dry DCOF >= 0.42

Product Shown
Breccia Imperiale 24"x48" Satin

Inspired by nature,
created by man.



Opustone[®]
STONE | TILE CONCEPTS

Fort Lauderdale | Miami | West Palm Beach